

NYLON 6

Polifil® NYLON 6 provides superior strength and rigidity with electrical resistance and surface lubricity. These properties have been proven to work in the following applications: automotive, bearings, and appliances. Standard processing techniques are applicable. Use this information as a guide to aid you in selecting the proper resin for your application. TPG will custom compound and fine-tune our formulations for your application.

PHYSICAL	ASTM / Method	Units	Polifil® 930L	Polifil® 836L
Reinforcement Content	TPG WI	%	0	0
Specific Gravity	D 792	-	1.13	1.09
Melt Flow	D 1238	g/10 min	n/a	n/a
Water Absorption, 24 Hours	D 570	%	1.6	1.3
Mold Shrinkage – 1/8” Specimen	D 955	in/in	0.012	0.012
MECHANICAL @ 73°F*				
Tensile Strength	D 638	psi	11,500	9,400
Elongation @ Yield	D 638	%	8	9
Elongation @ Break	D 638	%	40	60
Tensile Modulus	D 638	kpsi	440	360
Flexural Modulus (tangent)	D 790	kpsi	390	320
Flexural Strength	D 790	psi	15,000	12,000
Izod Impact (notched)	D 256	ft-lbs/in	1.1	2.5
Gardner Impact (1/2” tup)	D 5420	in-lbs	12	100
Rockwell Hardness	D 785	R-Scale	116	108
THERMAL				
Deflection Temperature, 66psi	D 648	°F	360	300
Deflection Temperature, 264psi	D 648	°F	145	140

**all properties tested dry as molded*



An ISO 9001 CERTIFIED COMPANY

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Mold shrinkage is intended as a guide only, as specific shrinkage is affected by part design, mold design and molding conditions. Therefore, The Plastics Group disclaims any liability for loss or damage incurred in connection with the use of this product.